



**Glass cloth and glass mat base epoxy resin
flame retardant copper clad laminate**

CEM-3-01PY

■ FEATURES

- Halogen, antimony, and red phosphorous free
- Flammability meets UL94V-0
- UV blocking type
- Wearing of drill bit is much less than that of FR-4, especially suitable for punch process
- UL file number E98983
- Through-hole reliability and warpage have been improved in order to replace some portions of the FR-4 market.
- IPC-4101C Specification is applicable.

■ PERFORMANCE LIST

Characteristics	Unit	Conditioning	Typical Values	SPEC	Test Method
Volume resistivity	MΩ-cm	C-96/35/90	5.0×10^8	$10^6 \uparrow$	2.5.17
Surface resistivity	MΩ	C-96/35/90	5.0×10^7	$10^4 \uparrow$	2.5.17
Permittivity 1MHZ	-	C-24/23/50	4.5	5.4 ↓	2.5.5.2
Loss tangent 1MHZ	-	C-24/23/50	0.020	0.035 ↓	2.5.5.2
Dielectric breakdown	KV	D-48/50	60 ↑	40 ↑	2.5.6
Moisture absorption	%	D-24/23	0.09	0.50 ↓	2.6.2.1
Flammability	-	C-48/23/50	94V0	94V0	UL94
Peel strength H oz	lb/in	288°C x 10" solder floating	8-10	6 ↑	2.4.8
Thermal stress	SEC	260°C dipping	200 ↑	40 ↑	2.4.13.1
Flexural strength	LW	N/mm ²	A	300-400	276 ↑
	CW	N/mm ²	A	200-300	186 ↑
Dimensional stability X-Y axis	%	E 0.5/170	<0.065	0.11 Max	2.4.39
Coefficient of thermal expansion					
Z-axis before Tg	ppm/°C	TMA	30-50	N/A	2.4.24
Z-axis after Tg	ppm/°C	TMA	220-320		
Glass transition temp	°C	DSC	105 ± 5	N/A	2.4.25
Punchability	Kg/cm ²	Shear strength ASTM D-732	1150	N/A	ASTM D-732
Comparative Tracking Index	V	Etched	600 ↑	N/A	ASTM-D3638
Decomposition Temperature (Td 5% W/L)	°C	TGA	310	N/A	2.4.24.6

Data shown are nominal values for reference only.

NOTE:

The average value in the table refers to samples of .062" 1/1.

Test method per IPC-TM-650

■ CERTIFICATION UL

- UL File No. : E98983
- ANSI TYPE:CEM-3